

# SonaKrete™ Acoustical Finish System Specification Guide 09 83 00

## PART 1 – GENERAL

### 1.01 Section includes

- A. SonaKrete acoustical finish system

### 1.02 Project Scheduling

- A. Clips, hangers, supports, sleeves and other attachments to the substrate are to be placed by other trades prior to application of acoustical finish
- B. Ducts, piping, conduit or other suspended equipment shall not be positioned until after the application

### 1.03 Submittals

- A. Submit one copy of the manufacturer's ISO 9001:2000 Certification
- B. Submit 2 copies of the test reports indicating compliance with the following:
  1. NRC values per ASTM C-423 conducted by a NVLAP certified testing laboratory:

Inches	250Hz	500Hz	630Hz	800Hz	1000Hz	2000Hz	4000Hz	NRC
1/4"	.07	.39	.54	.65	.69	.83	.87	.50
3/8"	.11	.46	.59	.70	.77	.84	.89	.55
1/2"	.16	.49	.66	.81	.89	1.03	.97	.65

2. Class 1 Fire Rating per ASTM E-84
- C. Submit one copy of the manufacturer's written certification that the materials contain no asbestos, fiberglass or other man-made mineral fibers.
  - D. Applicator's certificate: Manufacturer's approval of applicator.
  - E. Submit 2 5"x7" samples from the manufacturer.

### 1.04 Quality Assurance

- A. The manufacturer must be ISO 9001:2000 Certified.
- B. The Applicator: Approved by International Cellulose in performing the work of this Section.
- C. Field Samples:
  1. Construct one field sample panel, 10'x10', to specified thickness to illustrate texture and color.
  2. Prepare the sample using the same tools and techniques to be used for the actual application.
  3. Locate the sample where directed.

4. The applicator will inform the project architect when the sample is ready for review.
5. Do not start the actual application until the architect has approved the field sample.

#### **1.05 Delivery, Storage and Handling**

- A. Deliver in original, unopened containers bearing name of manufacturer and product identification.
- B. Store materials dry, off ground and under cover.
- C. Protect liquid adhesive, sealers & additives from freezing.

#### **1.06 Project Conditions**

- A. The air temperature in the room must be a minimum of 40° F and maintained until the material has cured.
- B. The substrate temperature must be a minimum of 40° F.
- C. The General Contractor to provide ventilation to ensure proper curing.

### **PART 2 – PRODUCTS**

#### **2.01 Acceptable Manufacturers**

- A. International Cellulose Corporation  
12315 Robin Boulevard  
Houston, Texas 77045  
(713) 433-6701 or (800) 444-1252  
Fax: (713) 433-2029

#### **2.02 Materials**

- A. SonaKrete™ Acoustical Finish System
- B. Iso-Prime
- C. Water-Potable
- D. Color shall be White

### **PART 3 – EXECUTION**

#### **3.01 Examination**

- A. Examine the substrate surfaces and report unsatisfactory conditions in writing. Do not proceed until unsatisfactory conditions are corrected.
- B. Drywall substrates require a minimum Level 3 finish and are to be sealed with Iso-Prime.
- C. Plaster substrates require a brown coat finish and are to be sealed with Iso-Prime.
- D. Consult International Cellulose for other substrates.

### **3.02 Preparation**

- A. Provide masking, drop cloths or other satisfactory coverings for materials/surfaces that are not to receive acoustical finish.
- B. Coordinate the installation of the acoustical finish with work of other trades.

### **3.03 Application**

- A. Install to a thickness to achieve an NRC of .65
- B. Install the acoustical finish according to the manufacturer's written instructions.
- C. After achieving the required thickness and while still wet, float the material to match the approved field sample.
- D. Cure the material with continuous natural or mechanical ventilation.

### **3.04 Protection**

- A. Protect finished installation under provisions of Division 1.